

**REMARKS**

Claims 11-28 are pending in this application. By this Amendment, the specification and abstract are amended, claims 1-10 are cancelled and claims 11-28 are new.

Should the Examiner believe that anything further would be desirable in order to place this application in even better condition for allowance, the Examiner is invited to contact the undersigned at the telephone number set forth below.

Respectfully submitted,



James A. Oliff  
Registration No. 27,075

Thomas J. Pardini  
Registration No. 30,411

JAO:TJP/cqc

Date: May 2, 2005

**OLIFF & BERRIDGE, PLC**  
**P.O. Box 19928**  
**Alexandria, Virginia 22320**  
**Telephone: (703) 836-6400**

DEPOSIT ACCOUNT USE AUTHORIZATION Please grant any extension necessary for entry; Charge any fee due to our Deposit Account No. 15-0461
--

# ABSTRACT OF THE DISCLOSURE

In forming a thin film of silver mirror on a surface of an object to be coated, a silver mirror reaction-treating solution including three solutions: an ammoniacal silver salt aqueous solution (I), an aqueous solution of caustic soda (IIa) and an aqueous solution of a carbohydrate-based reducing agent (IIb) such as glucose (fructose) are used. Immediately after the caustic soda aqueous solution (IIa) and the reducing agent aqueous solution (IIb) are mixed, the resulting mixed liquid and the ammoniacal silver salt aqueous solution (I) are independently and simultaneously sprayed onto the object. Alternatively, the mixed liquid (II) and the ammoniacal silver salt aqueous solution (I) are mixed together immediately upstream of a spraying nozzle, and the mixed liquid (III) is sprayed onto the object. Thereby, a thin film of silver mirror is formed in a thickness of around 0.01 to 0.03 μm, for example, through depositing silver by a silver mirror reaction.